



ELASTOMERIC CERAMIC with URETHANE  
**SATIN KOTE™**  
 INDUSTRIAL WATERPROOFING  
 SATIN FINISH PROTECTIVE COATING

**PRODUCT DATA**  
 15 YEAR LIMITED MATERIAL WARRANTY  
 #4035  
 06/20/07  
 superseding: 08/18/05

**PRODUCT DESCRIPTION:**

SATIN KOTE™ is a bright white, satin finish, elastomeric acrylic with urethane, insulating ceramic, Protective Waterproofing Coating and Industrial Maintenance Coating. An elastomeric acrylic urethane waterborne, latex based, high build formula that provides waterproofing, insulating, and soundproofing performance in a beautiful protective finish. Innovative technology combines an optimum blend of elastomeric, 100% acrylic and urethane resins to result in an extremely durable, waterproofing elastic film that has excellent resistance to thermal shock by expanding and contracting with hot and cold temperatures, but also has good impact resistance and excellent chemical resistance. A self-priming coating that forms a thick rubber like ceramic shield of protection that actually becomes part of the substrate due to excellent adhesion and bonding. SATIN KOTE™ offers superior mildew resistance, corrosion resistance, ceramic insulation & soundproofing, excellent adhesion, ultraviolet ray reflectivity and a beautiful satin finish. Excellent scratch and mar resistance. Qualifies for a CLASS A Fire Rating. Designed as an insulating, energy saving, industrial maintenance coating that will reduce costly maintenance, repairs and frequent repainting on most any surface or substrate. This easy to apply coating system will provide many years of durable protection and outstanding beauty. Available in a beautiful Matte Finish also; inquire about ULTRA KOTE™. A FIFTEEN YEAR LIMITED MATERIAL WARRANTY is available when product is applied according to Manufacturer's Specifications and a Warranty Registration is completed and approved within 90 days of application (see Warranty Compliance Information Below).

**PRODUCT USES:**

SATIN KOTE™ can be used on equipment, walls, pipes, holding tanks, roofs, etc. Excellent adhesion on most any surface including: weathered wood, shakes, plywood, clapboard, primed metal, galvanized, primed synthetic or aluminum siding, aluminum, tin, copper, asbestos, asphalt, urethane, polyester, primed Styrofoam, adobe, brick, stucco, concrete, clay, masonry, slate, slab and various other substrates. For interior or exterior use on residential, commercial and industrial applications.

**SURFACE PREPARATION:**

Trenching is necessary to form a complete seal. If applicable, trench 4 to 6 inches around the perimeter of the structure. Prepare Exterior Surfaces by thoroughly pressure washing with a water and chlorine solution (unless previously done before primer coat) using at least 1500 P.S.I. to remove any previous coatings, dirt, grease, and other foreign materials, especially mold, mildew and algae. SATIN KOTE™ will resist mildew growth, but will not kill mildew already on the surface. Clean Interior Surfaces by washing off all dirt, grease, soap and oil build-up with a powdered household cleaner and water. Rinse thoroughly. Remove loose paint and powdery substances. If after cleaning, there is still chalk present or existing coating is compromised, apply a coat of ULTRA PRIME™ Primer Sealer before the application of SATIN KOTE™. Patch any holes, cracks, seams, imperfections, etc., with PERMAPATCH™, Waterproofing Caulk & Sealant.

**Metal:** Clean surface of all grease, oil and foreign matter before priming. Rusted metal and uncoated metal must be primed with METAL-PRIME, a Red Iron Oxide Primer Sealer. Use a degreaser on galvanized or coated metals which have oils or surface treatments. Check SATIN KOTE™ adhesion on galvanized or coated metal by applying to a small area and evaluating after 48 hours. If lack of adhesion is present after evaluating, metal must be lightly scuffed without penetrating the coated finish or galvanizing. If applicable, use METAL-PRIME to spot prime the penetrated areas, then use ULTRA PRIME™ Primer for entire coated or galvanized surface.

**APPLICATION PROCEDURE:**

Stir well before using. Do not thin, use product as is. Do not apply when temperatures are below 45 degrees Fahrenheit or when humidity is very high. Do not apply when coating will be subjected to rain or heavy dew before it has had enough time to dry (approx. 2 to 4 hours). Drying time will vary depending on temperature, humidity and location. Apply using brush, roller or spray. Spread coating uniformly. Spread Rate will vary depending on surface. Apply each coat between 12 to 16 mils wet film thickness. Wait at least 12 hours before applying a second coat. Two coats resulting in a minimum 16 mil total dry film thickness are required for the FIFTEEN YEAR LIMITED MATERIAL WARRANTY.

**Airless Sprayers:** Use at least a 1 gallon per minute piston type airless sprayer with a minimum tip size of .025. Remove all line filters and gun filters before spraying.

**Clean Up:** Clean up all spills, tools and overspray immediately while the coating is still wet with warm soapy water.

**WARRANTY COMPLIANCE INFORMATION:**

The SATIN KOTE™ 15 YEAR LIMITED MATERIAL WARRANTY is for Product Only and applies to chipping, cracking and peeling, only. Labor is not covered by this warranty. This product is not guaranteed to stop or prevent leaks; all leaks must be repaired prior to the application of any coating. The WARRANTY is available only when product is applied according to Manufacturer's Application Procedures and Strict Material Requirement Specifications and a Warranty Registration (and a Job Completion Form if coated area exceeds 10,000 square feet) is submitted to Manufacturer within 90 days of completed coating application date (Application Procedure Sheets available upon request).

**MIL THICKNESS:** Primer is optional but recommended. Use either ULTRA PRIME™ for Walls or METAL-PRIME for exposed or unprimed Metal. The primer coat and two coats of SATIN KOTE™ must result in a minimum 20 mil total dry film thickness. If primer was not used, two coats of SATIN KOTE™ must result in a minimum 16 mil total dry film thickness.

**MINIMUM SPREAD RATES:** If optional primer coat was used, PRIMER must be applied at no more than 150 square feet per gallon. SATIN KOTE™ must be applied at no more than 150 square feet per gallon per coat, resulting in aggregate spread rate of 75 square feet per gallon.

Ambient Temperature of 77°F and RH of 50%

**TECHNICAL SPECIFICATIONS:**

Rates & Times May Vary Beyond Specifications

FINISH:	Satin	SPREAD RATE:	100 to 150 sq.ft./gal.
COLOR:	White, Deep & Clear Base	DRY to TOUCH:	2 to 4 Hours
VEHICLE TYPE:	Copolymer Emulsion	RECOAT:	12 Hours
SOLIDS by WEIGHT:	53% +/- 2%	CURE TIME:	5 to 7 Days
SOLIDS by VOLUME:	41% +/- 2%	SIZES:	1 Gal., 5 Gal., 55 Gal.
V.O.C.'s (averages):	n/a	GALLON WEIGHT:	11.1 lbs. +/- .3 lbs.

Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.

In Any Event Nationwide Chemical Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.



# MATERIALS HEALTH, SAFETY AND ENVIRONMENTAL DATA SHEET

**MSDS#:  
4035**

<b>Product Identification</b>	Product Name: <b>SATIN KOTE™</b> Product Code #: <b>4035</b> General Usage: Exterior Latex Elastomeric Coating General Description: Pigmented Latex Coating C.A.S. Number: None Established; Mixture	
<b>Manufacturer Information</b>	Manufacturer's Name: Nationwide Chemical Coating Mfrs., Inc. Address: 7106 24th Court East; Sarasota, FL 34243-3993 Emergency Telephone: 1-800-423-7264 or 941-753-7500 Information: 1-800-423-7264 or 941-753-7500 Web Site: www.nationwidecoatings.com E-Mail: info@natcoat.net Date Effective: January 1 <sup>st</sup> , 2005	
<b>Chemical and Physical Properties</b>	Color: White Physical State: Liquid Boiling Point: 212 Fahrenheit Specific Gravity (H <sub>2</sub> O=1): >1 Vapor Presence: about same as H <sub>2</sub> O Percent Volatile: 42-47% Evaporation Rate (Butyl Acetate=1): <1	Odor: Pungent Odor Odor Threshold: Unknown Melting Point: N/A Freezing Point: 32 Fahrenheit Solubility in H <sub>2</sub> O: Soluble pH (undiluted): 8 to 8.5 Vapor Density (Air=1): <1
<b>Fire Protection Information</b>	Decomposition/Combustion: N/A Flash Point: N/A; Does Not Burn Recommended Extinguishing Media: N/A Flammable Limits: N/A	
<b>Storage and Reactivity</b>	Hazardous Polymerization: Will Not Occur Storage Conditions: Keep from Freezing Toxic Products Which May Form: None	
<b>Transportation</b>	Hazard Classes: None; Not Hazardous Hazard Labels: Not Required Hazard Determination: MSD Sheet Shipping Containers: Varies Shipping Class: Class 55; Water Based Paint	
<b>Container Labeling</b>	Explanation of Unique Labeling System: None Used	

<b>Health Hazard Data</b>	<b>SHORT TERM EXPOSURE</b>	
	Route of Entry: Inhalation: Skin:  Eyes:  Ingestion:	Precautionary Treatment Expected None Expected None  Flush Immediately with large amounts of water for at least 15 minutes, holding eyelids open. Call a physician if irritation persists  Call a physician if significant amounts have been Swallowed. Give patient large amounts of water or milk for dilution.
	<b>LONG TERM EXPOSURE</b>	
	Carcinogen: Target Organ Effects: Other Health Hazards:	None None None Known
<b>Personal Protection</b>	Respiratory Protection: Protective Clothing: Ventilation: Other Protective Measures: Eye Protection:	No inhalation hazard expected None Required Local None Safety Glasses
<b>Spill or Leak Protection</b>	Accidental Release or Spill:  Neutralizing Chemical/Media:	Collect liquid or solidify with absorbent package for disposal  N/A
<b>Treatability</b>	Biodegradability: With water prior to cure. Influence on Biological Wastewater Treatment: None Other Impacts on Wastewater Treatment: None Recommended Wastewater Treatment: Dilutable Constituents Interfering With or Not Amenable to Biological or Wastewater Treatment: None	
<b>Recommended Waste Disposal</b>	Dispose of in accordance with Federal, State and Local guidelines.	